



Test Report

Number: SZHH00957934

Applicant: CSP INC
8248 W. ORANGE DR GLENDALE, AZ 85303 USA
Attn: WENDY

Date: May 12, 2015

Sample Description:

Three (3) pieces of submitted sample said to be :
Item Name : **Scrunchie Bracelet.**
Item No. : **K1-501.**
Applicant Specified Age : Over 3 Years.
Grading for Testing
Additional Material and Wet : No.
Paint Provided
Buyer : Kids' Korner.
Date Sample Received : May 07, 2015.



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued

Authorized by:
For Intertek Testing Services
Shenzhen Ltd.



Ben N.L. Lin
General Manager





Test Report

Number: SZHH00957934

Conclusion:

<u>Tested Samples</u>	<u>Standard</u>	<u>Result</u>
submitted samples	U.S. Consumer Product Safety Improvement Act 2008 Title I, Section 101 for total Lead content in surface coating	Not Applicable
Tested components of submitted samples	U.S. Consumer Product Safety Improvement Act 2008 Title I, Section 101 for Total Lead content in Non-surface coating materials (substrate)	Pass
submitted samples	U.S. CFR Title 16 Part 1303 total Lead content	Not Applicable

Authorized by:
For Intertek Testing Services
Shenzhen Ltd.



Ben N.L. Lin
General Manager





Test Report

Number: SZHH00957934

Tests Conducted

1 Total Lead (Pb) Content in Surface Coating

As per Standard Operating Procedure for Determining Lead (Pb) in paint and other similar surface coatings, test method CPSC-CH-E1003-09.1 was used and total Lead content was determined by Inductively Coupled Argon Plasma Spectrometry.

Assessment: Since no scrapable surface coating was found on the submitted samples, the testing scope was not applicable to the submitted samples.

2 Total Lead (Pb) Content in Non-Surface Coating Materials (Substrate)

As per Standard Operating Procedures for Determining total Lead (Pb) in children's products, test methods CPSC-CH-E1002-08.3 and/or CPSC-CH-E1001-08.3 were used and total Lead content was determined by Inductively Coupled Argon Plasma Spectrometry.

<u>Tested Component</u> (1)to(4)	<u>Result (ppm)</u> <10	<u>Limit (ppm)</u> 100
-------------------------------------	----------------------------	---------------------------

ppm = parts per million = mg/kg

Tested components:

Component lists:

- (1) Blue fabric with silver color plastic string insert (blue scrunchie bracelet).
- (2) Purple fabric with silver color plastic string insert (purple scrunchie bracelet).
- (3) Fuchsia fabric with silver color plastic string insert (fuchsia scrunchie bracelet).
- (4) White elastic string.

3 Total Lead (Pb) Content

As per U.S. Code of Federal Regulations Title 16 Part 1303, acid digestion method per ASTM E1613-04 / E1645-01 was used and total Lead content was determined by Inductively Coupled Argon Plasma Spectrometry.

Assessment : Since no scrapable surface coating was found on the submitted samples, the testing scope of 16 CFR 1303 was not applicable to the submitted samples.

End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

