

REPORT NO.: EFSN15050196C-C

DATE: MAY 13, 2015

PAGE: 1 of 3

TEST REPORT

: CSP INC **APPLICANT**

8248 W. ORANGE DR GLENDALE, AZ 85303 USA **ADDRESS**

3-D BOOKMARK **SAMPLE DESCRIPTION**

STYLE / ITEM NO. : K2-508

: KIDS' KORNER **BUYER**

AGE REQUESTED ON APPLICATION FORM

SAMPLE RECEIVED DATE : MAY 07, 2015

: MAY 07, 2015 TO MAY 12, 2015 **TEST PERIOD**

RESULT SUMMARY

TEST REQUESTED	RESULT
Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA).	PASS

SIGNED FOR AND ON BEHALF OF EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.

> Harry Chen Assistant Lab Manager

Horny Chen

Coco Luo Assistant Lab Manager

Seolus

This test report is valid for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.



REPORT NO.: EFSN15050196C-C

DATE: MAY 13, 2015

PAGE: 2 of 3

Material list

Testing material No.	Component	Material	Colour
1	Sticker on bookmark	Plastic/coating	White/multicolor
2	Bookmark	Plastic	Transparent
3	Rope	Textile	Yellow

Total Lead Content (CPSIA)

Test method : CPSC-CH-E1002-08.3

The sample was digested with acid. Then the lead content was determined by

Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit For surface coating materials: 90 ppm

For non-surface coating (substrate): 100 ppm

- according to US Consumer Product Safety Improvement Act 2008 (CPSIA

Sec.101).

Detection limit : 10 ppm

Test No.	Material No.	Test result (ppm)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.

Note: -1 mg/kg = 1 ppm = 0.0001%

- N.D. = Not Detected

Other Information / Remark:


- According to the customer's requirement, the appointed material has been tested.



REPORT NO.: EFSN15050196C-C

DATE: MAY 13, 2015

PAGE: 3 of 3



END OF THE REPORT