

TEST REPORT

APPLICANT : CSP INC
ADDRESS : 8248 W. ORANGE DR GLENDALE, AZ 85303 USA
SAMPLE DESCRIPTION : TOOL PEN
STYLE / ITEM NO. : K5-604
BUYER : KIDS' KORNER
AGE REQUESTED ON APPLICATION FORM : 3+
SAMPLE RECEIVED DATE : MAY 05, 2016
TEST PERIOD : MAY 06, 2016 TO MAY 11, 2016
RESULT SUMMARY :

TEST(S) REQUESTED BY APPLICANT:	RESULT
- Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA).	PASS
- Total Lead Content with reference to customer's requirement with regard to California Proposition 65.	PASS

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

SIGNED FOR AND ON BEHALF OF
EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.



Harry Chen
Assistant Lab Manager



Coco Luo
Assistant Lab Manager



This test report is valid for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts.
This test report does not entitle to carry any safety mark on this or similar products.

Material list

Testing material No.	Component	Material	Colour
1	Surface of ball pen	Coating	Silver
2	Surface of ball pen	Coating	Green
3	Surface of ball pen	Coating	Red
4	Lid of ball pen	Plastic	Translucence
5	Body of ball pen	Plastic	White
6	Tip of ball pen	Plastic	Silver and white
7	Refill	Plastic	Transparent
8	Refill	Liquid	Blue
9	Point	Metal	Silvery
10	Point(ball)	Metal	Silvery

Total Lead Content (CPSIA)

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3; CPSC-CH-E1003-09.1
 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit : For surface coating materials: 90 mg/kg
 For non-surface coating (substrate): 100 mg/kg
 - according to US Consumer Product Safety Improvement Act 2008 (CPSIA Sec.101).

Detection limit : 10 ppm

Test No.	Material No.	Test result (mg/kg)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	N.D.
Pb-6	6	N.D.
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	47
Pb-10	10	N.D.

Note: - 1 mg/kg = 1 ppm = 0.0001%
 - N.D. = Not Detected

TO BE CONTINUED

Eurofins Testing Technology (Shenzhen) Co. Ltd.

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: www.eurofins.com / www.pt.eurofins.com

Total Lead Content (California Proposition 65)

Test method : CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3; CPSC-CH-E1003-09.1
 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).

Limit For surface coating materials: 90 ppm
 For non-surface coating (substrate): 100 ppm
 - with reference to customer's requirement with regard to California Proposition 65.

Detection limit : 10 ppm

Test No.	Material No.	Test result (ppm)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	N.D.
Pb-6	6	N.D.
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	47
Pb-10	10	N.D.

Note: - 1 mg/kg = 1 ppm = 0.0001%
 - N.D. = Not Detected

Other Information / Remark:

According to the customer's requirement, the appointed materials have been tested.


TO BE CONTINUED

Eurofins Testing Technology (Shenzhen) Co. Ltd.

4/F, Building# 3, Runheng Dingfeng Industrial Park, No.1 Liuxian 3rd Road, Bao'an District, Shenzhen, P.R. China
 Tel.: +86 755 8358 5700 • Fax: +86 755 8358 5701 • Email: info.hk@eurofins.com • Website: www.eurofins.com / www.pt.eurofins.com

Photo Attachment

TOOL PEN



END OF THE REPORT