

# **TEST REPORT**

APPLICANT	:	CSP INC
ADDRESS	:	8248 W. ORANGE DR GLENDALE, AZ 85303 USA
SAMPLE DESCRIPTION	:	DOG PEN
STYLE / ITEM NO.	:	K7-611
BUYER	:	KIDS' KORNER
AGE REQUESTED ON APPLICATION FORM	:	3+
SAMPLE RECEIVED DATE	:	MAY 06, 2016; MAY 23, 2016
TEST PERIOD	:	MAY 06, 2016 TO MAY 26, 2016
RESULT SUMMARY	:	

TEST(S) REQUESTED BY APPLICANT:	RESULT
<ul> <li>Total Lead Content according to US Consumer Product Safety Improvement Act 2008 (CPSIA).</li> </ul>	PASS
<ul> <li>Total Lead Content with reference to customer's requirement with regard to California Proposition 65.</li> </ul>	PASS

SIGNED FOR AND ON BEHALF OF EUROFINS TESTING TECHNOLOGY (SHENZHEN) CO. LTD.

Hong Chen

Harry Chen Assistant Lab Manager

Cocoluo

Coco Luo Assistant Lab Manager



This test report is valid for the tested samples only. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.



## Material list

Testing material No.	Component	Material	Colour
1	Body of pen(white dog pattern)	Plastic/coating	Off white/multicolor
2	Body of pen(brown dog pattern)	Plastic/coating	Off white/black and brown
3	Body of pen(grey dog pattern)	Plastic/coating	Off white/multicolor
4	Lid of pen	Plastic	Transparent
5	Head of pen	Metal	Silvery
6	Penpoint	Metal	Silvery
7	Ball inside of Penpoint	Metal	Silvery
8	Refill	Plastic	Transparent
9	Ink	Ink	Black

\*\*\*TO BE CONTINUED\*\*\*



## **Total Lead Content (CPSIA)**

Test method	:	CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).
Limit	:	For surface coating materials: 90 mg/kg For non-surface coating (substrate): 100 mg/kg - according to US Consumer Product Safety Improvement Act 2008 (CPSIA Sec.101).

Detection limit : 10 ppm

Test No.	Material No.	Test result (mg/kg)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	81
Pb-6	6	56
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	N.D.

Note: - 1 mg/kg = 1 ppm = 0.0001% - N.D. = Not Detected

#### \*\*\*TO BE CONTINUED\*\*\*



# Total Lead Content (California Proposition 65)

Test method	: CPSC-CH-E1001-08.3; CPSC-CH-E1002-08.3 The sample was digested with acid. Then the lead content was determined by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES).
Limit	For surface coating materials: 90 ppm For non-surface coating (substrate): 100 ppm - with reference to customer's requirement with regard to California Proposition 65.

Detection limit : 10 ppm

Test No.	Material No.	Test result (ppm)
Pb-1	1	N.D.
Pb-2	2	N.D.
Pb-3	3	N.D.
Pb-4	4	N.D.
Pb-5	5	81
Pb-6	6	56
Pb-7	7	N.D.
Pb-8	8	N.D.
Pb-9	9	N.D.

Note: -1 mg/kg = 1 ppm = 0.0001%

- N.D. = Not Detected


# Other Information / Remark:

-According to the customer's requirement, the appointed materials have been tested.

\*\*\*TO BE CONTINUED\*\*\*



REPORT NO.: EFSN16050275C-C DATE: MAY 27, 2016 PAGE: 5 of 5



\*\*\*END OF THE REPORT\*\*\*